

International Standards		
International Standards	Symbol	Number
DIN EN 1652: 1998-03	CuZn30	CW505L
UNS*	C26000	*Unifield Numbering System (USA)

Chemical composition in %		
Element	min.	max.
Cu	69	71
Zn	Rest	-

Technical Data: Thickness 0.70 - 1.00 mm	
applicable width range	500 mm - 1000 mm
width tolerance	0 / + 2 mm
length tolerance for sheets	0 / + 10 mm
thickness tolerance	+/- 0.04 mm
longitudinal edge straightness tolerance - sheets up to 3000 mm - strips	up to 1 mm per 1000 mm, max. 3 mm for 3000 mm gauge length up to 1 mm per 1000 mm, max. 5 mm for 5000 mm gauge length
flatness (transverse to rolling direction)	< 0.2 % of strip width
Tensile strength (R _m)	270 - 350 N/mm ²
Proof Strength (R _{p0.2})	max. 160 N/mm ²
Elongation (A50)	≥ 40 %
hardness HV	80 - 90

Availability	
coil inside diameter Ø - big coil	500 mm
sheets	on request
surface	yellowish mill finish
temporary protective plastic film	foliation on one side
product application	construction

Physical Properties	
density	8.50 g/cm ³
coefficient of expansion	1.85 mm/m Δ T 100 K
modulus of elasticity at 20° C	122 kN/mm ²

To be read in conjunction with KME document "Important instructions for Storage, Application and Processing of TECU® Brass".

© = KME Germany GmbH & Co. KG

The technical information contained herein is correct and corresponds to the state-of-art at the time of printing.

Although all due care and attention has been taken, we cannot accept liability for the content.

KME Germany GmbH & Co. KG

Architectural Solutions

Klosterstraße 29, 49074 Osnabrück, Germany

Tel.: +49 (0) 541 / 321-2000

Fax: +49 (0) 541 / 321-2111

www.kme.com/tecu, info-tecu@kme.com