

# Delglaze<sup>®</sup> rooflight

Rooflight repairs  
**10 year guarantee**

---

## Onto a rooflight

### Preparation

#### All Edges

Any rooflights which are perished beyond structural safety should be removed and replaced with new.

Thoroughly clean any existing rooflights ensuring they are free from grease, fungus and mould growth.

An adhesion test should be carried out to any remaining well adhered coatings and existing rooflights. Most surfaces do not require priming however positive adhesion should be checked on non-standard surfaces. If necessary, prime with Sharmans PU primer.

**Note:** Do not at any time clean the surface with soap detergent. This action would leave a residual film and may adversely affect adhesion.

Check existing overlaps for excessive movement and insert additional fixings as necessary.

If the gap between the sheet is greater than 5mm a stitcher screw or rivet should be used to bring the sheets together.

Dry the lap using a mechanically driven blower ensuring the area between the rooflight and the roof sheet is thoroughly dry.

Ensure all surfaces to be treated are dry before the applying the coatings.

**Note:** This is an outline specification for the general application of this system. For a bespoke specification to deal with site complexities, please contact us.

**Disclaimer:** The information, and, in particular, the recommendations relating to the application and end-use of products, are given in good faith based on current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, unless from any written recommendations, or from any other advice offered by HD Sharman. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the Product Data Sheet for the product concerned, copies of which will be supplied on request.

HD Sharman Ltd. T. 01298 812371  
High Peak Works F. 01298 812237  
Chapel-en-le-Frith E. info@hdsharman.co.uk  
High Peak, Derbyshire W. hdsharman.co.uk  
SK23 0HW



**sharmans**  
gutter & roof refurbishment systems

Performance  
Coatings by

**Delvemade**