



## K Rend Standard Dash

Generated on 26.05.2020

### Detailed description

K Rend Standard Dash is a cement based and polymer modified self-coloured render system without the silicone properties, which is designed to receive a selection of dry dash finishes.

#### System includes:

A range of polymer modified basecoats for use as a backing for K Rend Standard Dash finish.

#### - Basecoats:

##### K Rend HP12 Base:

A "high polymer" basecoat for enhanced performance on difficult substrates. It is used over dense concrete or brickwork (with the use of R7 Acrylic Primer) as a primary coat for K Rend finishes. K Rend HP12 Base is Kitemarked to BS EN 998-1 and is IAB approved.

##### K Rend HPX Base:

A "high polymer" basecoat for ultra high performance onto unusual substrates which require greater flexibility and adhesion. It is used over lightweight blockwork (with alkali resistant reinforcing mesh incorporated) or brickwork (with the use of R7 Acrylic Primer) as a primary coat for K Rend finishes. K Rend HPX Base is Kitemarked to BS EN 998-1 and is IAB approved.

##### K Rend Standard UF Base:

A high quality, general purpose sprayable basecoat with excellent workability. It is used over 7 Newton, medium density concrete block as a primary coat for K Rend finishes. K Rend Standard UF Base is Kitemarked to BS EN 998-1 and is IAB approved.

##### K Rend UF Fibre Base:

A high quality, general purpose sprayable basecoat with excellent workability and increases impact resistance and tensile strength. It is used over 7 Newton, medium density concrete block as a primary coat for K Rend finishes. K Rend UF Fibre Base is Kitemarked to BS EN 998-1.

#### - Finish coat:

##### K Rend Standard Dash:

A self coloured dash receiver for hand application. It is applied over K Rend basecoats and is designed to receive a selection of dry dash finishes. Standard Dash is Kitemarked to BB EN 998-1 and is BBA approved.

### Product guidance - As Standard

#### Basecoat:

K Rend (Kilwaughter Minerals Ltd)



**K Rend (Kilwaughter Minerals Ltd)**  
Kilwaughter Minerals Ltd  
9 Starbog Road  
Larne  
County Antrim  
BT40 2TJ

Tel: +44 (0)28 2826 0766

[www.k-rend.co.uk](http://www.k-rend.co.uk)  
[sales@k-rend.co.uk](mailto:sales@k-rend.co.uk)



Various options available, the choice of basecoat is dependent upon substrate:

#### 7 Newton, medium density concrete blockwork:

##### - K Rend Standard UF Base or K Rend UF Fibre Base.

- Thickness: 8-10 mm.
- Coverage: 1.8 kg/ mm thick/ m<sup>2</sup> (14-18 kg/m<sup>2</sup> for 8-10 mm thickness).

#### Dense concrete:

##### - K Rend HP12 Base:

- Thickness: 6 mm.
- Coverage: 1.8 kg/ mm thick/ m<sup>2</sup> (8-11 kg/m<sup>2</sup> for 4-6 mm thickness).

#### Brickwork (choice of two basecoats available):

Prime using K Rend R7 Acrylic Primer (diluted 1:4 in water).

##### - K Rend HP12 Base.

- Thickness: 6 mm.
- Coverage: 1.8 kg/ mm thick/ m<sup>2</sup> (8-11 kg/m<sup>2</sup> for 4-6 mm thickness).

##### - K Rend HPX Base.

- Thickness: 6 mm.
- Coverage: 1.5 kg/ mm thick/ m<sup>2</sup> (6-9 kg/m<sup>2</sup> for 4-6 mm thickness).

#### Lightweight Block:

##### - K Rend HPX Base (with alkali resistant reinforcing mesh incorporated).

- Thickness: 6 mm.
- Coverage: 1.5 kg/ mm thick/ m<sup>2</sup> (6-9 kg/m<sup>2</sup> for 4-6 mm thickness).

#### Final coat:

- K Rend Standard Dash.
- Thickness (nominal): 8 mm (Thickness can vary according to the size of chip - normally = chip size + 2 mm).
- Coverage: 1.5 kg/ mm thick/ m<sup>2</sup> (10-15 kg/m<sup>2</sup> for 6-10 mm thickness).
- Finish: Dry dash aggregate (4-12 mm) from approved source as selected by the specifier.

#### Total thickness (finished):

- 16 mm for application onto blockwork.
- 14 mm for all other backgrounds.



## Options

### Colour:

Available in a range of 20 colours.

## Product specification

### Manufacturer

- Name: K Rend (Kilwaughter Minerals Ltd)
- Web: [www.k-rend.co.uk](http://www.k-rend.co.uk)
- Email: [sales@k-rend.co.uk](mailto:sales@k-rend.co.uk)
- Tel: +44 (0)28 2826 0766
- Fax: +44 (0)28 2826 0136
- Address: Kilwaughter Minerals Ltd,9 Starbog Road,Larne,County Antrim BT40 2TJ

**Product reference** K Rend Standard Dash

**Primer** Not required  
K Rend R7 Acrylic Primer - For brickwork substrate.

- Type K Rend HP12 Base  
K Rend HPX Base  
K Rend Standard UF Base  
K Rend UF Fibre Base

- Thickness 6 mm  
8-10 mm

### Final coat

- Type K Rend Standard Dash

- Thickness 8 mm

- Colour Arran  
Buttermilk  
Champagne  
Cinnamon  
Cream  
Fintry Stone  
Green  
Grey  
Ivory  
Oatmeal  
Pewter Grey  
Polar White  
Powder Blue  
Salmon Pink  
Sandstone



Sterling White  
Stone  
Terracotta  
White  
York

- Finish

Dry dash aggregate - Washed and  
graded aggregate from an approved  
source as selected by the specifier.

**Total thickness (finished)**

14 mm  
16 mm